

CI/SfB | Yq4 |
 Issue 5 September 2021
 (SUPERSEDES Issue 4 May 2014)

General Information



Factory produced silo mortars offer a range of mix proportions and overcome many potential problems relating to site mixing.

The transportable silo is filled by the producer with a pre-batched mixture of dried fine aggregate (sand), cement, lime if required and other admixtures or pigments premixed to the customer's requirements.

The silo is delivered to site complete with integral mixer. Once power and water supplies are connected, mortar can be produced as required. The rate at which water is added can be controlled to achieve the required consistency.

Factory produced silo mortar for masonry

Composition and Manufacture

MPA Mortar members manufacture their factory produced mortars with fine aggregates conforming to the requirements of BS EN 13139, cements conforming BS EN 197-1, admixtures to BS EN 934-3 and when incorporated, lime to BS EN 459-1. If required, pigments conforming to BS EN 12878 can be accurately added at the factory to produce an extensive range of colours and shades.

The following table gives the mix designation, compressive strength (BS EN 998-2 mortar class) and composition.

The compressive strength of prescribed mortars will vary according to a number of factors, particularly the type of sand that is used, but historically there has been an empirical relationship which has been used in arriving at Table 1. For these traditional mixes, although a mortar class is given in the table, the strength of a prescribed mortar should not be used as the basis of conformity with the standard. If a definite strength is required of a mortar, then a designed mix should be used or the mortar manufacturer should be consulted.

Table 1: Mixes for prescribed masonry mortars and mortar classes

Mortar designation	Prescribed mortars (traditional proportion of materials by volume) ^A				Mortar class that may be assumed	Suitable for use in environmental condition
	Cement ^B : lime : sand with or without air entrainment	Cement ^B : sand with or without air entrainment	Masonry cement ^C : sand	Masonry cement ^D : sand		
(i)	1:0 to 1/4 :3	1:3	Not suitable	Not suitable	M12	Severe (S)
(ii)	1:1/2 :4:4 1/2	1:3 to 4	1:2 1/2 to 3 1/2	1:3	M6	Severe (S)
(iii)	1:1:5 to 6	1:5 to 6	1:4 to 5	1:3 1/2 to 4	M4	Moderate (M)
(iv)	1:2:8 to 9	1:7 to 8	1:5 1/2 to 6 1/2	1:4 1/2	M2	Passive (P)

^A When the sand portion is given as, for example, 5 to 6, the lower figure should be used with sands containing a higher proportion of fines, whilst the higher figure should be used with sands containing a lower proportion of fines

^B Cement or combinations as detailed in the National Annex BS EN 998-2

^C Masonry cement (organic filler other than lime) as detailed in the National Annex BS EN 998-2

^D Masonry cement (lime) as detailed in the National Annex BS EN 998-2

Properties

In respect of fresh properties the manufacturer is required to declare the workable life and, where relevant, the chloride content and air content.

For the hardened properties of design masonry mortars the compressive strength shall be declared and where relevant the bond strength, water absorption and density. In addition the water vapour permeability and thermal conductivity are required to be declared by reference to tabulated values.

For prescribed mortars the mix proportions by volume or by weight of all the constituents shall be declared by the manufacturer. In addition, the indicative compressive strength shall be declared with reference to clause NA.1 of the National Annex to BS EN 998-2 and PD 6678.

Selection of Mortar Mix

The mortar should be selected by reference to the European Code of Practice Eurocode 6; BS EN 1996.

Durability

Factory produced ready-to-use mortars are of guaranteed composition, thoroughly mixed and will therefore provide satisfactory performance. However, this does not negate the designer's responsibility to specify the correct mortar designation for the type of structure, exposure conditions and type of masonry units. Neither does it relieve the builder of his responsibility to ensure that operatives use site best practice. Recommendations are given in other data sheets in this series and the manufacturers' technical literature should be followed.

Working Characteristics

In hot conditions some stiffening may occur which may be corrected by the addition of a small amount of water followed by trowel mixing on the spot board in the traditional manner. Once the initial set has started the

mortar must not be reconstituted in a mechanical mixer or by any other method.

The setting of mortar is affected by weather and will proceed more slowly when it is colder.

It is inadvisable to proceed with the construction of masonry whilst the temperature is below 3°C and falling.

Protective Measures

All mortar should be protected against excessive rain or drying conditions.

All newly erected masonry should be covered at the end of a working day or when rained off.

No further measures are required in respect of factory produced mortars beyond those recognised as being good site practice.

Maintenance

Generally, factory produced mortars require the minimum of maintenance.

References	
BS EN 197-1	Cement composition, specification and conformity criteria for common cements
BS EN 459-1	Building lime, definitions, specifications and conformity criteria
BS EN 934-2	Concrete admixtures - definitions, requirements, conformity, marking and labelling
BS EN 934-3	Admixtures for masonry mortar - definitions, requirements, conformity, marking and labelling
BS EN 998-2	Specification for mortar for masonry - Part 2: Masonry mortar
BS EN 1015	Methods of test for mortar for masonry
BS EN 1996	Eurocode 6, Design of masonry structures, design consideration, selection of materials and execution of masonry
BS EN 12878	Pigments for the colouring of building materials based on cement and/or lime, specifications and methods of test
BS EN 13139	Aggregates for mortar
BS 4551	Methods of testing mortars, screeds and plasters
PD 6678	Guide to the selection and specification of masonry mortar
PD 6682-3	Aggregates for mortar - guidance on the use of BS EN 13139

All references to British and/or European standards should refer to the current published edition.

For a comprehensive list of British and European Standards see the MPA Mortar data sheet of technical references.



MPA Mortar is part of the Mineral Products Association, the trade association for the aggregates, asphalt, cement, concrete, dimension stone, lime, mortar and silica sand industries.

Mineral Products Association Ltd
Gillingham House
38 - 44 Gillingham Street
London SW1V 1HU
Tel +44 (0)20 7963 8000
Fax +44 (0)20 7963 8001
mick.russell@mineralproducts.org
www.mortar.org.uk

Factory produced mortar products will contain either cement or lime, both of which have properties which are hazardous to health. Please refer to the manufacturers or suppliers Material Safety Data Sheet for the specific product/grade to find more information on the nature of the hazardous properties, the risks and health effects of exposure and the recommended safe use and handling procedures.